



Air Distribution Concepts 204 Hallberg Street Delavan, WI 53115 Ph: 262-728-6860 www.adctubes.com

Technical Data
Preliminary
9440B UVI #2

4.0 Mil
LDPE

<u>Film Properties</u>	<u>ASTM Method</u>	<u>Units</u>	<u>Typical Value</u>
Melt Index	D-1238	g/10 Min.	2
Density	D-1505	g/cm	0.923
Haze	D-1003	%	12
Gloss	D-2457	%	65
Tensile Strength(Break)	D-882	PSI	
MD			3,200
TD			2,800
Ultimate Elongation	D-882	%	
MD			550
TD			775
Secant Modulus(1%)	D-882	PSI	
MD			27,500
TD			31,500
Dart Impact	D-1709	Grams	225

NOTICE: All statements, information and data given herein are believed to be accurate and reliable. This data is presented without guaranty, warranty or responsibility of any kind, expressed or implied.

Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

The above typical values are intended as guides only and not as specification limits.